



Euro Polymers (GB) Ltd.

Wychwood House,
3 Saxton Lane,
Leeds,
LS9 8HE.
Tel: 01132 456999
Fax: 01132 456444
info@europolymers-gb.com

Product Profile No.10

EUROBOND Bitumen Primer

EUROBOND IS A LIQUID APPLIED, LOW VISCOSITY BITUMEN SOLUTION.

Eurobond is used to prime concrete, brickwork and blockwork prior to the application of Euroseal membranes and other bitumen coatings. Applied by brush, roller or airless spray.

Applied By:



1. Applications

In conjunction with waterproofing systems for:

- Roofs
- Floor Slabs
- Tunnels
- Internal Wet Areas
- Basements

2. Cost Benefits

- Highly penetrative. Strengthens porous substrates.
- Simple and rapid application.
- Over coat in 2 hours in ventilated conditions.
- Provides Temporary waterproofing until subsequent coatings are applied.

4. Typical Physical & Performance Data

Form:	Black Liquid	Solvent Type:	Aromatic Hydrocarbon
Specific Gravity:	0.90	Overcoat Time:	2 - 4 hours
Non Volatile Content:	55%	Maximum Service Temperature:	80° c

5. Installation

Substrates

- New concrete, screed or render should have a brushed or wood float finish, and should be free from contamination by any material which could impair adhesion. All surface defects should be repaired by approved methods. Protrusions greater than 3 mm should be removed.
- Existing concrete, screed or render should be well prepared to provide a dense, defect free substrate.
- Brickwork, blockwork and masonry should be flush pointed.
- All substrates should be dry.

Application

Apply using a wide nylon brush, sheepskin disposable rollers or airless spray. The product must not be applied in wet conditions. Clean tools using white spirit or Hydrocarbon solvent.

Coverage Rates

Dense Concrete	0.125 litres/m ²
Porous Concrete	0.25 litres/m ²
Lightweight Screed	0.5 litres/m ²

Euro Polymers Technologies Ltd.

Tel : + 44 1706 879888

Fax: +44 1706 879888

info@europolymers.com

Euro Polymers (GB) Ltd.

Tel: 01132 456999

Fax: 0 1132 456444

info@europolymers-gb.com

Euro Polymers Middle East & North Africa

Tel: + 203 429 0284

Fax: + 203 429 5015

sahab@europolymers.com

Euro Polymers Asia

Tel: + 601 2322 8880

Fax: + 603 7660 7539

btemplar@europolymers.com